

CONFIDENTIAL

LCP Film

Special Solution Casting Technology
Thermotropic Liquid Crystalline Polyester Film



슈퍼 엔지니어링 플라스틱「LCP」의 특징

【KGK LCP의 특성】



방향족 폴리에스테르 계 수지로서 방향족으로써의 강직성·내열성을 지니며 폴리에스테르로써의 결정성의 높기 의하여 강도를 지닌 용융상태(아몰퍼스)로 규칙이 올바르게 분자가 나열된 성질을 지닌다。

LCP의 장점은 슈퍼 엔지니어링의 특징인 내열성·고강도(결정성)。
LCP 독자적인 장점인 가스배리어성과 고주파에서 저유전·고절연특성。
LCP는 KGK의 독자적인 장점인 용융상태(아몰퍼스)에서 배향하는 성질(중심이 편심 됨에 의하여 강도 등의 특성을 언밸런스화)을 소거하기 위하여 용융성형(Melt molding)이 아닌 용융 캐스팅 법(Solution casting method)(용매를 이용한 성형)에 의한 부드러움과 높은 강도특성

KGK Special solution casting method(KGK특허 용융 캐스팅 법)으로 만들어진 Liquid crystal polymer film (액정 폴리머 필름)、불리우며、


특수용액 캐스팅 용융 액정성 방향족 폴리에스테르 필름
(Special Solution Casting Thermotropic Liquid Crystalline Polyester Film)

LCP for FPC, FCCL



FCCL configuration	Relative permittivity (1MHz)
Polyimide	3.3
Epoxy adhesive	3.5~5.0
LCP	≤ 3.0

各種基板用材料の特性




【LCP란】

저유전, 저유전 정접이라하며 우수한 전기특성에 더하여 저흡수와 내열, 성형성도 함께 겸비한 LCP는 고속통신에 결함이 없는 수지재료. 유동방향의 선팽창율은 금속수준으로 플렉시블 기판(FPC)용도로는 동박과의 상성이 우수함. 차세대 고속통신 5G나 자동차의 밀리파 레이더용 FPC용도가 예상이 됨.

CONFIDENTIAL

사양

Structure:



Sizes:

Products	Thickness(μm)	Color	Standard Roll Size
SAR 13	13	Brown	300mm x 20M
SAR 20	20		
SAR 25	25		
SAR 30	30		
SAR 35	35		

***Please inquire for more different thickness and width**



CONFIDENTIAL

Property

품번	단위	조건	수치
전기 특성			
비유전율 특성	-	1GHz	3.09
체적 저항율	$\Omega \cdot \text{cm}$	23°C	39×10^{17}
흡수 특성			
흡수율	ppm/°C	85°C/85%RH@168hr	< 0.1
기계 특성			
인장강도	Mpa	25°C	60 ^{*1}
인장탄성율	Mpa	25°C	3000 ^{*1}
신율	%	25°C	7 ^{*1}
내열성			
납땜 내열성	-	270°C/30 sec	PASS
		300°C/3 sec	PASS
융점	°C	DSC method	316
열전도율	W/m · K	-	0.38

*1 Aneling : 300°C/60min

LCP for FPC, FCCL



FCCL(LCP//Copper Multi layer film)

특징:

우수한 내열성

저흡습성

250°C

가스배리어성

높은 인장강도와 탄성율 특성

필름의 등방성

용도:

FPC 기판

LED 기판

Sizes:

Products	Thickness	Structure	Standard Roll Size
SAR25C12	0.037	LCP(25 μ m)//Copper(12 μ m)	300mm × 20M

***Please inquire for more different thickness and width**

CONFIDENTIAL

LCP Film

Special Solution Casting Technology Thermotropic Liquid Crystalline Polyester Film

User is responsible for determining whether the KGK product is fit for a particular purpose and suitable for user's method of application.

Please remember that many factors can affect the use and performance of a KGK product in a particular application.

The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a KGK product. Given the variety of factors that can affect the use and performance of a KGK product, some of which are uniquely within the user's knowledge and control. It is essential that the user evaluate the KGK product to determine whether it is fit for a particular purpose and suitable for the user's method of application. KGK make no warranties on above data.



KGK Chemical Corp.
940 Minaminagai Tokorozawa-City Saitama-Pref
359-0011 Japan
Tel : +81 4 2944 5151
Mail : info-k@kgk-tape.co.jp
URL : <http://www.kgk-tape.co.jp/>